

Description

T732, polypropylene primer, is a one component primer that primarily increases the adhesion of adhesives in combination with plastics.

T732 provides good adhesive strength in combination with diverse plastics, especially polypropylene.

Characteristics

Viscosity @ 23°C	Approx. 10 mPa.s
Density	Approx. 870 kg/m ³
Solid content	Approx. 2.5%
Drying time	Min. approx 15 min and max. approx. 30 minutes
Processing temperature	+ 5°C to + 35°C
Storage temperature	+ 5°C to + 35°C
Temperature resistance	-30°C to + 90°C

Apply the primer with a brush onto the surface and let it evaporate. The surface has to be dry and free of dust and grease.

Packaging and storage

Bottle: 50 mL, 250 mL, 1L

Storage life: 24 months in unopened original packaging

PRECAUTIONS: This product and the auxiliary materials normally combined with it are capable of producing adverse health effects ranging from minor skin irritation to serious systemic effects. None of these materials should be used, stored, or transported until the handling precautions and recommendations as stated in the Material Safety Data Sheets (MSDS) for this and all other products being used are understood by all persons who will work with the product.