

# Technical Data Sheet

## Silicone Rubber Sheetting General Purpose Solid



### Material


General Purpose Silicone Rubber



### Available Grades

GP 30, GP 40, GP 50, GP 60, GP 70, GP 80

### Temperature Range



## General Information

Our colour range has been tested to and is in accordance with the American Food and Drugs Administration (FDA) 21 CFR 177-2600, BFR XV Empfehlung and colour bleed test according to BFR Empfehlung part B 11 & Directive EC 1935/2004.

Translucent, Blue, White, Red and Black 40° Shore to 70° Shore have been approved by the WRAS (Water Regulations Advisory Service) for use in contact with potable water at temperatures up to 85°C (185°F).

These products meet the flammability requirements of FAR 25/JAR 25/CS 25 Appendix F, Part 1, (a)(1)(iv) and (a)(1)(v) horizontal flammability test and Automotive Standard PART 571MVSS302.

## Environmental Resistance

Silicone rubber products have an excellent resistance to:

- Ozone
- Oxidation
- Ultraviolet light
- Corona discharge
- Cosmic radiation
- Ionising radiation
- Weathering in general

This information and our technical advice, whether verbal, in writing or by way of trials, is given in good faith but without warranty. This also applies where proprietary rights are involved. Our advice does not release you from the obligations to check its validity and to test our products as to their suitability for their intended use. The storage, application and use of our products are beyond our control and, therefore, entirely your own responsibility. Our products are sold in accordance with our General Conditions of Sale. The information contained within this data sheet is subject to change without notice. Issue date 01.01.2019.

**SILEX SILICONES LTD**

Silex Ltd, Unit 10, Oakhanger Farm Business Park, Oakhanger, Bordon, Hampshire, GU35 9JA. Tel 00 44 1420 470360, Fax 00 44 1420 472802

E-Mail: [sales@silex.co.uk](mailto:sales@silex.co.uk), Website: [www.silex.co.uk](http://www.silex.co.uk), Registered company number: 1951973. Place of registration: England & Wales. Directors: K Soudah, S.J. Fearn, P Millson, Ray Soudah

# Technical Data Sheet

Silicone Rubber Sheetting General Purpose Solid



## Availability Format

- Supplied in continuous roll lengths
  - Widths of 1000mm and 1200mm (standard), 1000mm x 1000mm for 15mm+
  - 1500mm and 1800mm on request
  - Pressure sensitive adhesive backing
- Punched and water jet gaskets
  - Slit strips
  - Full range of standard colours
  - Capability to colour match

## Typical Applications

- Automotive
  - Domestic & Commercial
  - Catering
  - Electronics
- Construction
  - Energy
  - Food & Beverage
  - Heating and Ventilation (HVAC)
- Industrial
  - Insulation
  - Lighting
  - Marine

## Mechanical Properties

		GP20	GP 30	GP 40	GP 50	GP 60	GP 70	GP 80	Test Method
Property	Units	Typical Value	Typical Value	Typical Value	Typical Value	Typical Value	Typical Value	Typical Value	
Hardness	Shore A ±5	20	30	40	50	60	70	80	DIN ISO 7619-1
Tensile Strength	Mpa (PSI)	10,1 (1464)	8.0 (1150)	9.0 (1300)	9.0 (1300)	10.0 (1450)	10.0 (1450)	7.0 (1015)	ISO 37 type 2
Elongation to Failure	%	979	500	525	450	400	320	215	ISO 37 type 2
Tear Strength	N/mm (lb./in.)	25,0 (142)	16.0 (91)	23 (130)	18 (100)	22 (125)	20 (115)	17 (88.5)	ASTM D624 die B
Compression Set 24 Hrs @ 150°C	%	23	23	25	15	13	9	18	DIN/ISO 815 type B
Compression Set 22 Hrs @ 300°F	%	-	20	22	16	10	10	16	ASTM D395 method B type 2

This information and our technical advice, whether verbal, in writing or by way of trials, is given in good faith but without warranty. This also applies where proprietary rights are involved. Our advice does not release you from the obligations to check its validity and to test our products as to their suitability for their intended use. The storage, application and use of our products are beyond our control and, therefore, entirely your own responsibility. Our products are sold in accordance with our General Conditions of Sale. The information contained within this data sheet is subject to change without notice. Issue date 01.01.2019.

SILEX SILICONES LTD

Silex Ltd, Unit 10, Oakhanger Farm Business Park, Oakhanger, Bordon, Hampshire, GU35 9JA. Tel 00 44 1420 470360 , Fax 00 44 1420 472802  
E-Mail: [sales@silex.co.uk](mailto:sales@silex.co.uk), Website: [www.silex.co.uk](http://www.silex.co.uk), Registered company number: 1951973. Place of registration: England & Wales. Directors: K Soudah, S.J. Fearn, P Millson, Ray Soudah

# Technical Data Sheet

Silicone Rubber Sheetting General Purpose Solid



## General Characteristics

Test	Result	Standard
Brittle Point	-80°C (-112 °F)	ASTM D746
Limiting Oxygen Index	24.0 %	BS 2782 Part 1
Thermal Conductivity	0.24 W.m <sup>-1</sup> .K <sup>-1</sup>	VDE 0304
Radiation Resistance	>10 <sup>5</sup> Grays (10 <sup>7</sup> Rads) typical	
Dielectric Strength	23 kV.mm <sup>-1</sup>	VDE 0303
Dielectric Constant	2.9	VDE 0303
Dissipation Factor	3x10 <sup>-4</sup>	VDE 0303
Volume Resistivity	3x10 <sup>15</sup> Ω.cm	VDE 0303

## Accreditations

- FDA 21 CFR 177-2600 compliant
- BfR compliant
- EU 1935/2004
- WRAS compliant
- FAR 25/JAR 25/CS 25 Appendix F, Part 1, (a)(1)(iv) (a)(1)(v) horizontal flammability test
- Automotive Standard PART 571MVSS302
- REACH compliant and ROHS compliant

## Additional Information

This information and our technical advice, whether verbal, in writing or by way of trials, is given in good faith but without warranty. This also applies where proprietary rights are involved. Our advice does not release you from the obligations to check its validity and to test our products as to their suitability for their intended use. The storage, application and use of our products are beyond our control and, therefore, entirely your own responsibility. Our products are sold in accordance with our General Conditions of Sale. The information contained within this data sheet is subject to change without notice. Issue date 01.01.2019.

SILEX SILICONES LTD

Silex Ltd, Unit 10, Oakhanger Farm Business Park, Oakhanger, Bordon, Hampshire, GU35 9JA. Tel 00 44 1420 470360 , Fax 00 44 1420 472802  
E-Mail: [sales@silex.co.uk](mailto:sales@silex.co.uk), Website: [www.silex.co.uk](http://www.silex.co.uk), Registered company number: 1951973. Place of registration: England & Wales. Directors: K Soudah, S.J. Fearn, P Millson, Ray Soudah